

**Paper quality WY/ WV/ WR/ WN/ WA/ SK**

**TECHNICAL CHARACTERISTICS**

	Grammage	g/m <sup>2</sup>	160	170	180	190	200	210	+/- 3 %
UNE/EN/ISO - 536	Moisture Content	%	10,0	10,0	10,0	10,0	10,0	10,0	+/- 1,0 %
UNE/EN - 20287	Dry Tensile Strength MD	Kg	19,0	20,0	21,5	21,5	22,5	22,5	-10 %
UNE/EN/ISO - 1924/2	Dry Tensile Strength CD	Kg	6,4	6,5	7,5	7,5	8,5	8,5	-10 %
UNE/EN - 20535	Cobb 60 F	g/m <sup>2</sup>	25	25	25	25	25	25	MAX.30
UNE/EN - 20535	Cobb 60 B	g/m <sup>2</sup>	25	25	25	25	25	25	MAX.35
UNE - 57066/3	Gurley	s	70	70	70	70	70	70	MAX.90
ISO 2470-1	Whiteness	%	52	52	52	52	52	52	MIN.48
ISO 16260	Ply Bond	J/m <sup>2</sup>	270	270	270	270	270	270	MAX.325/ MIN.250

**MD:** Machine Direction | **CD:** Crosswise Direction | **F:** Front | **B:** Back

UNE/EN/ISO - 20187	SAMPLE CONDITIONING	
	Relative Humidity	50 +/- 2 %
	Temperature	23 +/- 1°C

COMMENTS
• For grammages other than the nominal ones indicated, the immediately lower grammage values will be applied.