

AB Paper Quality

TECHNICAL CHARACTERISTICS

	Grammage	g/m ²	70	80	90	100	110	120	
UNE/EN/ISO - 536	Moisture Content	%	8.0	8.0	8.0	8.0	8.0	8.0	+/- 1.5
UNE/EN/ISO - 287	Elongation MD	%	2.0	2.0	2.0	2.0	2.0	2.0	-10 %
UNE/EN/ISO - 1924-2	Elongation CD	%	5.5	5.5	5.5	5.5	5.5	5.5	-10 %
UNE/EN/ISO - 1924-2	Tensile Strength MD	m	6,000	6,000	6,000	6,000	6,000	6,000	-10 %
UNE/EN/ISO - 1924-2	Tensile Strength CD	m	2,500	2,500	2,500	2,500	2,500	2,500	-10 %
UNE/EN - 21974	Tearing Strength MD	mN m ² /g	8.5	8.5	8.5	8.5	8.5	8.5	indicative
UNE/EN - 21974	Tearing Strength CD	mN m ² /g	10.5	10.5	10.5	10.5	10.5	10.5	indicative
UNE/EN - 20535	Cobb 60 F	g/m ²	25	25	25	25	25	25	MAX.40
UNE/EN - 20535	Cobb 60 B	g/m ²	25	25	25	25	25	25	MAX.40
UNE - 57066-3	Gurley	s	50	55	60	65	70	75	indicative

MD: Machine Direction | **CD:** Crosswise Direction | **F:** Front | **B:** Back

TOLERANCES

- Grammage +/-4% up to 100g/m², +/-3% up to 120g/m²
- Moisture content +/- 1.5%
- Elongation and Tensile Strength -10%
- Cobb F and B maximum 40g/m²

Headquarters

Diputació 238, 5^o 8^a • 08007 Barcelona • Tel. +34 933 042 860 • Fax +34 933 014 481

Paper mill

Km. 10 de la carretera N-230 de Lleida al Valle de Arán • 25124 Rosselló (Lleida)
SPAIN

alier@aliersa.com • www.aliersa.com